

MULTI-BASE Solvent Basecoat MMG1 - MMG5

Description:

This is a solvent based basecoat for industrial use along with off road vehicles. This basecoat features good basecoat loading giving full coverage in 2 coats providing the correct undercoat is used.

Available as a sole binder or pigmented to any colour.

Preparation	The substrate should be prepared in a usual manner making sure that repairs are smooth.
Mixing Ratio	1:1 with Multi-thinner basecoat or 2k universal thinner
Number of coats	2 Full coats
Flash off time	5 minute flash off time minimum between coats and 10 minutes before baking.
Viscosity	For best results viscosity should be between 16-18 seconds.
Spraying	2 bar spraying pressure with a 1.2 or 1.3 setup spray gun. Set before application to see what setup suits the painter best.

Completed on: 07/07/2020

The information on the document is provided to the best of our knowledge and as a guide only and We are not liable for any problems that may arise from using this product. We have tested all our products with each other in laboratory conditions and have passed all testing. Any faults that may arise from miss use or using with other brands is done so at your own risk.