

MULTI-CRYL 2K Direct Gloss MMG1 - MMG5

Description:

This is a 2K HS Compliant topcoat that can be tinted to any colour. This Direct Gloss is a two-coat application with 2 full coats. This binder, when ordered with pigment (as ready mixed colour) has good pigment loading so 2 coats should provide good coverage providing the correct colour primer is used.

Preparation	The substrate should be prepared in a usual manner making sure that repairs are smooth.
Mixing Ratio	2:1 optional 5-10% thinner but best results are without thinner
Number of coats	2 Full coats
Flash off time	5 minute flash off time minimum between coats and before baking
Drying time	A range of hardeners are available for this clearcoat MMH1/ Standard for 30 minute bake MMH1/ Fast for 20-25 minute bake MMH1/ Extra fast for 15-20 minute bake
Handling	Allow for up to a 1 hour cool down time before sanding and polishing. This 2K Gloss is designed to be easy to polish for a few days before becoming more scratch resistant. This does not affect the Gloss levels over time
VOC	This Direct Gloss meets the 420g/l VOC Requirements

Completed on: 07/07/2020

The information on the document is provided to the best of our knowledge and as a guide only and We are not liable for any problems that may arise from using this product. We have tested all our products with each other in laboratory conditions and have passed all testing. Any faults that may arise from miss use or using with other brands is done so at your own risk.